



Temporary  
Surface  
Protection



Dust &  
Noise  
Control



Hoardings  
& Barrier  
Systems

## PRODUCT DATA SHEET

### BUBBLE BOARD

#### Technical Information

Tensile Strength at Yield	Kg/cm <sup>2</sup>	290	D638
Elongation at Yield	%	10	D638
Flexural Modulus	Kg/cm <sup>2</sup>	13500	D790B
Notched Izod Impact Strength at 23°C	Kg.cm/cm	13	D256A
Heat Deflection Temperature at 4.6 kg/cm <sup>2</sup>	°C	85	D648
Rockwell Hardness	R scale	82	D785A
Drop weight impact at -29°C	Kg.com	280	Internal Method
Water absorption after 24 hours	%	0.02	D570

Values shown are average and are not to be considered as specifications

SYDNEY (HEAD OFFICE)  
13 Rachael Cl,  
Silverwater NSW, 2128  
(02) 9334 2999  
[sales@protectagroup.com.au](mailto:sales@protectagroup.com.au)  
Warehouse: 30 Fariola St,  
Silverwater NSW, 2128

MELBOURNE  
3 Saligna Drive,  
Tullamarine VIC, 3043  
(03) 9002 2899  
[VICsales@protectagroup.com.au](mailto:VICsales@protectagroup.com.au)

BRISBANE  
99 Holt St (Cnr Chapman Pl),  
Eagle Farm QLD, 4009  
(07) 3363 3799  
[QLDsales@protectagroup.com.au](mailto:QLDsales@protectagroup.com.au)

PERTH  
51 Wittenberg Dr,  
Canning Vale WA, 6155  
(08) 6269 6999  
[WAsales@protectagroup.com.au](mailto:WAsales@protectagroup.com.au)