

Slip Check to AS 4586-2013 Protecta Site Mat XTRA

Report Number: R23892.1

This report replaces report R23892

Report Date: 22 June 2021

Total Number of Pages 2

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

Issued by

Safe Environments Pty Ltd
Unit 4, 40 Bessemer Street
Blacktown NSW 2148

Prepared for

Protecta Group
13 Rachael Close
Silverwater NSW 2128

Approved by



Dale Rowell
Authorised Signatory

22 June 2021

Test Report No. R23892.1

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Protecta Group
 Client Address: 13 Rachael Close
 Silverwater NSW 2128
 Product Manufacturer: Supplied by Protecta Group
 Product Description: Rhino Site Mat

Test conducted according to: AS 4586:2013 Appendix A
 Location: 4/40 Bessemer Street, Blacktown NSW 2148
 Conducted by: Ola Crouch

Date: 21 June 2021 Temperature: 17°C
 Sample: Unfixed Cleaning: None
 Rubber slider used: Slider 96 Conditioned: Grade P 400 paper dry followed
 Slope of specimen: Tested on a flat level surface by wet lapping film
 Direction of Test: NA

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	46	46	47	44	48

Reported SRV of Sample:	46
Class:	P4

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd